

Red Clay Bodies – Cone 04

Brick Red Joining Slip (Cone 06-6)

Cedar Heights Goldart 39.88
Cedar Heights Redart 39.88
Calcined Kaolin 15.96
Barnard Slip 2.90
Red Iron Oxide .80
Sodium Silicate .58

Brick Red Clay Body Good for hand building (Cone 06-6)

Ball Clay 12.80
Cedar Heights Goldart 34.50
Cedar Heights Redart 34.50
Medium Grog 7.1
Fine Grog 7.1
Barnard Slip 2.51
Red Iron Oxide .59

Red Earthenware C/04

Cedar Heights Redart	71.4
Ball Clay	10.7
Flint	10.7
Feldspar	7.2

Helaine Ettinger's C/04 Terra Cotta

Cedar Heights Redart	60
Cedar Heights Goldart	15
Pine Lake Fireclay (30-mesh)	15
Talc	10
Barium Carbonate	0.75

Red Earthenware (Cone 06-5)

Talc	10
Ball Clay	25
Cedar Heights Redart	10
Fireclay	80
Omulgee Clay	5 lbs.
Grog	133 lbs.

George's Carbondale Clay (Cone 6)

Custer Feldspar	8%
A. P. Green Fireclay	30
CC Ball Clay	12
Carbondale Red Clay	40
Cone	10

14625 Earthenware Clay Body (Cone 04-05)

Newman Red Clay	80 lbs.
Redart Clay	25 lbs.
Fire Clay	10 lbs.
Medium Grog	15 lbs.
Nepheline Syenite	2 lbs.

	02)	7.92 %
Clay	11.88	
Carbondale Clay	39.61	
Fireclay	29.70	
Grog	10.89	
	100.00 %	

Add 25% Cedar Heights Redart for a darker body to be used in oxidation.

Terra-Cotta Sculpture Body 1 (Cone 1)

Talc	5 %
Cedar Heights Goldart	10
Cedar Heights Redart	65
Fireclay	10
Tennessee Ball Clay	10
	100%

Terra-Cotta Sculpture Body 2 (Cone 1)

Talc	5 %
Cedar Heights Goldart	15
Cedar Heights Redart	50
Fireclay	20
Tennessee Ball Clay	10
	100%

John Frantz' C/03-1 Red Clay

Cedar Heights Redart

Fireclay

Ball Clay

Talc

Lincoln Fireclay	50
A.P. Green Fireclay	50
Red Art	75
Talc	25
Grog	25
Ball Clay	25
Nylon Fiber	hand

EARTHENWARE TILE CLAY cone 04

Lincoln Fireclay	50
A.P. Green Fireclay	50
Red Art	75
Talc	25
Grog	25
Ball Clay	25
Nylon Fiber	hand

T. VOGEL CLAY BODY cone 04-1

Red Art	75
Apache	30
A.P. Green	30
Talc	25
	30
	10

Carbondale Red 27.28
Grey 12.84
Nick's Slur 10.12
CT 30 9.22
Neph Sy 30.03
Iron 42.84 1.55
Whiting 8.97

Schnabel Terra Cotta Clay (Cone 3)	
Talc	10%
A. P. Green Fireclay	10
Cedar Heights Redart	50
Kentucky Ball Clay (OM 4)	10
Medium Grog	10
Silica Sand	10
	100%
Add: Red Iron Oxide	1%
Bentonite	2%

Redware Body (Cone 03)	
Cedar Heights Goldart	30.0%
Cedar Heights Redart	50.0
Tennessee Ball Clay #5	20.0
	100.0%
Add: Grog	1.5%

NOTKIN 9/1 REDWARE

RED ART	6340
Red IRON OXIDE	912
BALL CLAY	4560

50 20 20 12 5 5 5 10 5

Terracotta
Redart
TX Sagger
fireclay
flint
talc
spodumene
neph 57
fine grog
barium carb.

Archie Bray Black G.

Red Art	50
OM4	25
Mang. Dio	15
Black Stain	12
Black Iron	5
Barium Carb	pinch

Terra Cotta (Joh. Gill)

Red Art	50
Gold Art	20
Calvert	10
Pine Lake	10
Talc	10
Barium Carb.	1/2